

HALAR® thin gauge films Data Sheet

Halar® ECTFE is a semi-crystalline and melt-processable fluoropolymer resin manufactured by Solvay Solexis. Because of its chemical structure - a 1:1 alternating copolymer of ethylene and chlorotrifluoroethylene - Halar® ECTFE offers a unique combination of properties.

Ajedium's Halar® film is a strong, hard, tough, abrasion resistant film that retains its useful properties over a broad range of temperatures. Its low-temperature properties, especially those related to impact, are particularly outstanding. Halar® ECTFE films also have good tensile, flexural and wear resistant properties.

In addition, Halar® ECTFE films have demonstrated excellent weathering properties and are extremely resistant to UV radiation and common industrial or environmental pollutants.

Halar® film is an excellent barrier to water vapor in a wide range of temperatures. This lower permeability is a key advantage in applications where protection from water as well as oxygen or other small gaseous molecules is required.

Halar® ECTFE films exhibit high bulk and surface resistivity, high dielectric strength, low dielectric constant, and moderate dissipation factor. The dissipation factor varies slightly with frequencies above 1 kHz. The dielectric constant of Halar® is stable across broad temperature and frequency ranges.

MANUFACTURING

Halar® ECTFE transparent films are extruded by Ajedium in a wide range of thicknesses, widths and lengths. Surface treated films are also available.

For further information on Halar® films produced by Ajedium Films, a division of Solvay Solexis, Inc. contact your Solvay Solexis representative or go to www.ajedium.com.

HALAR® TRANSPARENT THIN GAUGE FILMS TYPICAL PROPERTIES

	Test Method	Typical Values	
		SI Units	US Customary Units
Physical and Thermal Properties			
Density	ASTM D-1505	1.66-1.70 g/cm ³	132-135 lb/ft ³
Thickness Range		25-200 µm	1-8 Mil
Melting Point	ASTM D-3418	240-244 °C	464-471 °F
Thermal Conductivity @ 40 °C (104 °F)	ASTM C-177	0.15 W/(m·K)	0.9 BTU-in/(h·ft ² ·°F)
Water Vapor Transmission Rate @ 38°C (100°F) and 90% RH For a 50 µm film Cast film	ASTM F-1249	1.6 g/m ² -d	
Mechanical Properties		MD TD	MD TD
Stress at Break @ 23 °C (73 °F)	ASTM D 882	53 MPa 50 MPa	7700 psi 7300 psi
Elongation at Break @ 23 °C (73 °F)	ASTM D 882	280 % 280 %	280 % 280 %
Modulus @ 23 °C (73 °F)	ASTM D 882	1550 MPa 1500 MPa	225 kpsi 218 kpsi
Shrinkage		MD TD	MD TD
Free shrink % @ 200°C	30 min in oven	4.4 % 0 %	4.4 % 0 %
Electrical Properties			
Surface Resistivity at 23°C	ASTM D 257	> 10 ¹⁷ Ohm	> 10 ¹⁷ Ohm
Volume Resistivity	ASTM D 257		
@ 23°C – 73°F		6·10 ¹⁶ Ohm-cm	6·10 ¹⁶ Ohm-cm
@ 80°C – 176°F		4·10 ¹⁵ Ohm-cm	4·10 ¹⁵ Ohm-cm
@ 130°C – 266°F		2·10 ¹³ Ohm-cm	2·10 ¹³ Ohm-cm
Dielectric Constant at 1 kHz	ASTM D 150		
@ 23°C - 73°F		2.5	2.5
@ 100°C - 212°F		2.6	2.6
Dissipation factor at 1 kHz	ASTM D 150		
@ 23°C - 73°F		1·10 ⁻³	1·10 ⁻³
@ 100 °C – 212°F		2·10 ⁻³	2·10 ⁻³

To our actual knowledge, the information contained herein is accurate as of the date of this document. However neither Solvay Solexis S.p.A., nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Solexis S.p.A., reserves the right to make additions, deletions or modifications to the information at any time without prior notification.

Trademarks and/or other Solvay Solexis S.p.A. products referenced herein are either trademarks or registered trademarks of Solvay Solexis S.p.A. or its affiliates, unless otherwise indicated.

Copyright 2009, Solvay Solexis S.p.A. All Rights Reserved. – Document no. A01E003