

SOLEF® PVDF films Data Sheet

SOLEF® Polyvinylidene fluoride (PVDF) homopolymer is a semi-crystalline and melt-processable fluoropolymer that, because of its chemical structure, offers peculiar combination of properties.

Ajedium's SOLEF® PVDF film is chemically inert to most acids, aliphatic and aromatic organic compounds, chlorinated solvents, alcohols, etc. Moreover, it has very high purity, abrasion resistance comparable to that of polyamides, and relatively low coefficient of friction.

SOLEF® PVDF film can be used within a wide range on temperatures and has excellent intrinsic fire resistance.

Moreover, polyvinylidene fluoride films have demonstrated excellent weathering properties and are extremely resistant to UV radiation and common industrial or environmental pollutants.

PVDF can cover a wide range of possible applications. Some examples are: release films, filters, chemical resistant lining, outdoor UV resistant as well as electric and electronic applications.

MANUFACTURING

SOLEF® PVDF homopolymer films are extruded by Ajedium in a wide range of thicknesses, widths and lengths.

For further information on PVDF films produced by Ajedium Films, a division of Solvay Solexis, Inc. contact your Solvay Solexis representative or go to www.ajedium.com.

SOLEF® PVDF (HOMOPOLYMER) FILMS TYPICAL PROPERTIES

	Test Method	Typical Values	
		SI Units	US Customary Units
Physical and Thermal Properties			
Yield	internal	565 m ² /kg/μm	15,625 in ² /lb/mil
Melting Point	ASTM D-3418	170-174 °C	338-345 °F
Mechanical Properties			
		MD TD	MD TD
Stress at Yield @ 23 °C (73 °F)	ASTM D-882	55 MPa 56 MPa	8,000 psi 8,100 psi
Elongation at Yield @ 23 °C (73 °F)	ASTM D-882	6 % 6.2 %	6 % 6.2 %
Stress at Break @ 23 °C (73 °F)	ASTM D-882	57 MPa 54 MPa	8,300 psi 7,800 psi
Elongation at Break @ 23 °C (73 °F)	ASTM D-882	200 % 250 %	200% 250%
Modulus @ 23 °C (73 °F)	ASTM D-882	2,000 MPa 2,100 MPa	290 kpsi 305 kpsi
Shrinkage			
		MD TD	MD TD
Free shrink % @ 130°C	30 min in oven	0.7 % 0 %	0.7 % 0 %
Free shrink % @ 150°C	30 min in oven	1.4 % 0.2 %	1.4 % 0.2 %
Electrical Properties			
Volume Resistivity @ 23°C – 73°F	ASTM D 257	7.7·10 ¹⁴ Ohm-cm	7.7·10 ¹⁴ Ohm-cm
Dielectric Constant @ 1 kHz 23°C (73°F)	ASTM D 150	7.6	7.6

To our actual knowledge, the information contained herein is accurate as of the date of this document. However neither Solvay Solexis S.p.A., nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Solexis S.p.A., reserves the right to make additions, deletions or modifications to the information at any time without prior notification.

Trademarks and/or other Solvay Solexis S.p.A. products referenced herein are either trademarks or registered trademarks of Solvay Solexis S.p.A. or its affiliates, unless otherwise indicated.

Copyright 2009, Solvay Solexis S.p.A. All Rights Reserved. – Document no. A02E001