

## Polyphenylsulfone (PPSU) films Data Sheet

Polyphenylsulfone (PPSU) is an amorphous thermoplastic material that offers exceptional hydrolytic stability, and toughness superior to other commercially-available, high-temperature engineering films.

PPSU films have high deflection temperatures and outstanding resistance to environmental stress cracking.

Moreover, PPSU films are steam sterilizable with high retention of impact properties.

The polymer is inherently flame retardant, and also has excellent thermal stability – making films suitable for applications where very low shrink at high temperatures are needed – and good electrical properties.

PPSU films are widely used in different applications including electrical/electronic, aircraft interiors, automotive industry.

### MANUFACTURING

PPSU films are extruded by Ajedium in a wide range of thicknesses, widths and lengths.

*For further information on Polyphenylsulfone films produced by Ajedium Films, a division of Solvay Solexis, Inc. contact your Solvay Solexis representative or go to [www.ajedium.com](http://www.ajedium.com).*

# AJEDIUM PPSU FILM

Ajedium Films, division of Solvay Solexis, Inc.  
 100 Interchange Blvd. Newark, DE 19711  
 Tel: +1-302-452-6609  
 Fax: +1-302-452-6610  
 Email: kathleen.cerchio@solvay.com

## PPSU FILMS TYPICAL PROPERTIES\*

	Test Method	Typical Values	
		SI Units	US Customary Units
<b>Physical and Thermal Properties</b>			
Glass Transition Temperature	ASTM D-3418	220 °C	428 °F
Water Absorption @ 50°C (122°F), 75%RH, 24 hrs	ASTM D-570	0.4 %	0.4 %
Yield	internal	770 m <sup>2</sup> /kg/μm	21,308 in <sup>2</sup> /lb/mil
<b>Mechanical Properties</b>		<b>MD TD</b>	<b>MD TD</b>
Stress at Yield @ 23 °C (73 °F)	ASTM D-882	68 MPa 59 MPa	9,900 psi 8,600 psi
Elongation at Yield @ 23 °C (73 °F)	ASTM D-882	9.2 % 6.8 %	9.2 % 6.8 %
Stress at Break @ 23 °C (73 °F)	ASTM D-882	92 MPa 70 MPa	13,400 psi 10,100 psi
Elongation at Break @ 23 °C (73 °F)	ASTM D-882	143 % 102 %	143 % 102 %
Modulus @ 23 °C (73 °F)	ASTM D-882	1,590 MPa 1,980 MPa	231 kpsi 287 kpsi
Dart impact	ASTM D-1709	538 g	1.18 lb
Tear Propagation	ASTM D-1922	10 gforce 9 gforce	0.022 lbf 0.020 lbf
Tear Resistance	ASTM D-1004	857 gforce 930 gforce	1.89 lbf 2.05 lbf
<b>Electrical Properties</b>			
Dielectric Strength	ASTM D-149		4,900 V/mil
Dielectric constant @ 1MHz	ASTM D-150	1.38	1.38

\* Reported values were measured on a 25μm thick film

To our actual knowledge, the information contained herein is accurate as of the date of this document. However neither Solvay Solexis S.p.A., nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Solexis S.p.A., reserves the right to make additions, deletions or modifications to the information at any time without prior notification.

Trademarks and/or other Solvay Solexis S.p.A. products referenced herein are either trademarks or registered trademarks of Solvay Solexis S.p.A. or its affiliates, unless otherwise indicated.

Copyright 2009, Solvay Solexis S.p.A. All Rights Reserved. – Document no. A14E002